

PATENT ABSTRACTS OF JAPAN

(11)Publication number : **2000-319434**

(43)Date of publication of application : **21.11.2000**

(51)Int.Cl.

C08J 9/00

(21)Application number : **11-127568**

(71)Applicant : **NITTO DENKO CORP**

(22)Date of filing : **07.05.1999**

(72)Inventor : **YAMAMURA TAKASHI**

YAMAMOTO KAZUNARI

HANABUSA KENJI

SHIRAI HIROYOSHI

KIMURA MUTSUMI


SAKAKIBARA YASUHIKO

(54) PRODUCTION OF POROUS MOLDING


(57)Abstract:

PROBLEM TO BE SOLVED: To easily obtain a high-porosity, a large-pore-diameter molding in a desired shape by dissolving a porous moldable polymer in a solvent under heating, allowing the obtained polymer solution to gel by treatment with a gelling agent, and immersing the gel in a poor solvent for the polymer to extract the solvent therefrom.

SOLUTION: The porous moldable polymer used is desirably the one having a number-average molecular weight of 50,000-500,000 and is exemplified by PS, polymethyl methacrylate, polyethylene



I



II

glycol, or PE. The gelling agent used is desirably at least one member selected from an amino acid derivative and a cyclohexanediamine derivative, more desirably, at least either of Z-L-Ile-NHC18H37 of formula I and a cyclohexane derivative of formula II. It is desirable that after the solvent is removed by extraction, the gel is further immersed in a solvent capable of extracting the gelling agent to remove the gelling agent therefrom by extraction. In this way, for example, a porous molding having a porosity of 50-95% and a pore diameter of 0.5-60 μm or a molding having a thickness of several mm to several tens mm or of at least 100 mm can be obtained.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

* NOTICES *

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

PRIOR ART

[Description of the Prior Art] There are many methods among the manufacture methods of a porosity molding object, and it is already used in the field of much industry. For example, after dissolving the polymer which can dissolve in water and the dissolving solvent with a solvent and considering as a polymer solution, it casts on a support base material, Coacervation is formed by being immersed in underwater [which is the poor solvent of polymer]. To the method and polymer which carry out extract clearance of the solvent and acquire a porosity molding object, CaCO_3 , SiO_2 etc., after adding and kneading a particle, extruding in the shape of a film and adding a drawing process depending on the case How to remove a particle and form a porosity molding object using the solvent which dissolves a particle, Moreover, after mixing and kneading the solvent of a non-volatile like a liquid paraffin to polymer, extruding in the shape of a film and adding a drawing process depending on the case, it is the poor solvent of polymer and there is the method of removing a solvent with the solvent which can extract remove a solvent, and forming a porosity molding object etc. Although all of these methods are effective in processing of the shape of a comparatively thin sheet, only what also has a comparatively small aperture is difficultly obtained by making thick sheets and a thick three-dimensional Plastic solid. Especially the porosity molding object acquired with a wet method had the problem that it was difficult to make a skin on a front face, or to become fine porosity, and to acquire the porosity molding object of the big aperture as a molding object.

[0003] As a method of on the other hand acquiring a porosity molding object, although the method of using as a hole the crevice which sinters a polymer particle, welds between particles and is formed between particles is developed, generally the polymer supplied with a particle-like gestalt in this method, especially the polymer of ultrahigh molecular weight are not used, and general-purpose polymer cannot necessarily be used. According to this method, the porosity molding object which suited the mold freely using metal mold etc. is also producible, but the non-filling section of the grain child with whom restoration of a particle does not go well at the time of molding is made, and molding of a complicated form etc. is difficult in the poor flow of a particle in making a defect.

[0004] Therefore, it was difficult to produce a porosity molding object using general-purpose polymer, and especially the thing to acquire for a big aperture and a high void content was difficult. Moreover, still sufficient technology is not known about how to produce the porosity molding object which has a complicated configuration.

[Translation done.]